

17301 Ridgeland Avenue Tinley Park, IL 60477

Customer Service: 800-777-3300

TDS: Effective Date: Revision: GMH6 04/23/10 2

## **Technical Data Sheet**

# **Turn Tell Label**

This specification is intended to outline the physical and chemical properties of *PANDUIT*'s pressure sensitive self-laminating clear polymer label that can be rotated and repositioned after installation and include the following part numbers and printable material identifiers:

| Part Number Prefixes |  |  |  |
|----------------------|--|--|--|
|                      |  |  |  |
|                      |  |  |  |
|                      |  |  |  |

| Printable Material Suffixes |     |  |  |
|-----------------------------|-----|--|--|
| V1T                         | V3T |  |  |
| V1C                         | V7T |  |  |
| V2T                         | V8T |  |  |

#### **PRODUCT SPECIFICATIONS:**

Description: Material is RoHS compliant (European Union directive 2002/95/EC).

Material is a top coated polymer film with a pressure sensitive

adhesive. This material is intended for interior and exterior markings

and used in a self-laminating format for wire/cable marking.

Print Methods: This material is recommended for thermal transfer printing.

Adhesive: Acrylic based, pressure sensitive adhesive.

Standard Colors: Clear film with colored print-on area

Thickness: 4.5 +/- 0.5 mils (substrate and adhesive)

Service Temperature Range: -40°F to 200°F (-40°C to 107°C)

Minimum Application Temperature:  $50^{\circ}F (10^{\circ}C)$ 

Storage Conditions: Store at 70°F (21°C) and 50% Relative Humidity.

P1 cassettes should not be stored in direct sunlight, or temperatures exceeding

95°F.

#### PROPERTIES: PERFORMANCE:

Peel Adhesion to Stainless Steel: 32 oz/in width minimum (PSTC-1, 15 min. dwell)

Shear Adhesion: 3 hours minimum (PSTC-7, Procedure A)
Tensile Strength: MD 55 +/- 5.5 lbs./inch width (PSTC-31)

Elongation: MD 110% +/- 10% (PSTC-31)

UV Resistance: 3000 hours no change observed (ASTM G53)

Elevated Temperature Exposure: After 8 hours at 150°F (65.5°C) there was no deterioration of the substrate

Page 1 of 2 © 2009 PANDUIT Corp

TDS: GMH6

17301 Ridgeland Avenue Tinley Park, IL 60477

Customer Service: 800-777-3300

TDS: Effective Date: Revision:

GMH<sub>6</sub> 04/23/10

### **Technical Data Sheet**

#### **CHEMICAL/SOLVENT RESISTANCE:**

Samples were thermal transfer printed with RMR4BL and RMH4BL ribbon. These samples were wrapped around a 1/12" OD wire in self-laminating format. Test was conducted at room temperature after 24 hour dwell. The samples were immersed in the specified chemical reagents for 5 immersions using the following cycle: a 10 minute immersion time followed by a 30 minute recovery time.

|                                  | Visual Observation   |   |
|----------------------------------|----------------------|---|
| Chemical Reagent                 | Substrate / Adhesive | Thermal Transfer<br>Printed Legend<br>RMR4BL & RMH4BL |
| Distilled Water                  | No effect            | No effect   |
| Mineral Spirits                  | No effect            | No effect   |
| ASTM #3 Oil                      | No effect            | No effect   |
| Isopropyl Alcohol                | No effect            | No effect   |
| Methanol                         | No effect            | No effect   |
| 3% Alconox Detergent             | No effect            | No effect   |
| 10% Sodium<br>Hydroxide Solution | No effect            | No effect   |
| 10% Sulfuric Acid<br>Solution    | No effect            | No effect   |
| 5% Sodium Chloride<br>Solution   | No effect            | No effect   |
| Freon TF                         | No effect            | No effect   |
| Super Agitene                    | No effect            | No effect   |
| Jet-A Fuel                       | No effect            | No effect   |
| Arco TruSlide 68                 | No effect            | No effect   |
| SAE 30 Motor Oil                 | No effect            | No effect   |

#### **LIMITED WARRANTY**

All PANDUIT Identification Solution Products (except for Software programs) are warranted to be free from defects in material and workmanship at the time of sale but our obligation under this warranty is limited to replacement of the product proved to be defective within 6 months from the date of sale, or in the case of printers, within 90 days from the date of sale. This warranty is void if the products or printers are modified, altered or misused in any way. Use of PANDUIT printers with any product other than the specified PANDUIT products for which the printer was designed constitutes misuse. Before using, the user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers or seller and manufacturer.

NEITHER PANDUIT OR SELLER SHALL BE LIABLE FOR ANY OTHER INJURY, LOSS OR DAMAGE, WHETHER DIRECT OR CONSEQUENTIAL. ARISING OUT OF THE USE OF, OR THE INABILITY TO USE THE PRODUCT OR THE PRINTER.

THIS WARRANTY IS MADE IN LIEU OF AND EXCLUDES ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OF PARTICULAR USE ARE SPECIFICALLY EXCLUDED.

The information contained in this literature is based on our experience to date and is believed to be reliable. It is intended as a guide or use by persons having technical skill at their own discretion and risk. We do not guarantee favorable results or assume any liability in connection with its use. Dimensions contained herein are for reference purposes only. This publication is not to be taken as a license to operate under, or a recommendation to infringe any existing patents. This supersedes and voids all previous literature, etc.

Page 2 of 2 © 2009 PANDUIT Corp

TDS: GMH6